

Product Information

**VESTAKEEP® 4000 FP**

**UNREINFORCED, HIGH-VISCOSITY POLYETHER ETHER KETONE FINE POWDER**



**VESTAKEEP® 4000 FP** is an unreinforced, highviscosity polyether ether ketone fine powder. It can be used as a basic resin or in blends with different additives for manufacturing compression molding parts.

The semi-crystalline polymer features superior thermal and chemical resistance. VESTAKEEP® 4000 FP is of low flammability.

VESTAKEEP® 4000 FP is supplied as powder in boxes with moisture-proof polyethyleneliners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may affect values.

For guidance processing of VESTAKEEP® 4000 FP please follow the general recommendations in our brochure “VESTAKEEP® High Performance in Powder Form Polyether Ether Ketone Powders”.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT [EVONIK-HP@EVONIK.COM](mailto:EVONIK-HP@EVONIK.COM) OR VISIT OUR PRODUCT AT [WWW.INDUSTRIAL.VESTAKEEP.COM](http://WWW.INDUSTRIAL.VESTAKEEP.COM)

**Key Features**

**Industrial Sector**

Automotive and Mobility, Aircraft and Aerospace

**Resistance to**

Heat (thermal stability), Fire / burn

**Processing**

Press and sintering

**Conformity**

Food contact

**Delivery form**

Powder

**Additives**

Unfilled

**Mechanical properties ISO**

	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile modulus	<b>3500</b>	MPa	ISO 527
Tensile strength	<b>96</b>	MPa	ISO 527
Yield stress	<b>96</b>	MPa	ISO 527
Yield strain	<b>5</b>	%	ISO 527

Stress at break	<b>77</b>	MPa	ISO 527
Nominal strain at break, tB	<b>30</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-
Charpy notched impact strength, -30°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-

<b>Thermal properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Melting temperature	<b>340</b>	°C	ISO 11357-1/-3
Temp. of deflection under load A, 1.80 MPa	<b>150</b>	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	<b>205</b>	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	<b>335</b>	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	<b>305</b>	°C	ISO 306
Melting Temperature	<b>340</b>	°C	ASTM D 3418

<b>Physical properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1300</b>	kg/m <sup>3</sup>	ISO 1183
Moisture content	<b>0.18</b>	Gew.-%	ISO 15512
Bulk density, Granulate	<b>273</b>	kg/m <sup>3</sup>	-
Density	<b>1300</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Burning Behav.</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Burnin behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-

<b>Rheological properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Melt volume-flow rate, MVR	<b>11</b>	cm <sup>3</sup> /10min	ISO 1133

Temperature	<b>380</b>	°C	-
Load	<b>5</b>	kg	-

Powder properties	dry	Unit	Test Standard
Bulk density, powder	<b>250</b>	g/l	EN ISO 60
Particle size, D(50)	<b>60</b>	µm	ISO 13320, DIN ISO 8130-13

## Characteristics

### Applications

Electrical and Electronical

### Processing

Electrostatic coating

### Special Characteristics

Semi-crystalline, High viscosity

### Color

Natural color

### Delivery form

Fine powder (FP)

### Chemical Resistance

General chemical resistance

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

\* is a registered trademark of Evonik Industries AG or one of its subsidiaries

**Evonik Operations GmbH**  
**Smart Materials**  
**High Performance Polymers**  
 45772 Marl / Germany  
 Tel: +49 2365 49-9878  
[evonik-hp@evonik.com](mailto:evonik-hp@evonik.com)  
[www.plastics-database.com](http://www.plastics-database.com)