

Product Information

# VESTAKEEP® 4000 G BK

## HIGH VISCOSITY, UNREINFORCED POLYETHER ETHER KETONE



**VESTAKEEP® 4000 G BK** is a high viscosity, unreinforced polyether ether ketone for injection molding and extrusion.

The semi-crystalline polymer features superior, thermal and chemical resistance. Parts made from VESTAKEEP® 4000 G BK are of low flammability.

VESTAKEEP® 4000 G BK can be processed by common machines for thermoplastics.

We recommend a melt temperature between 380°C and 400°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

VESTAKEEP® 4000 G BK is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

Pigmentation may affect the values.

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

For information about processing VESTAKEEP® 4000 G BK, please follow the general recommendations in our brochure "VESTAKEEP® PEEK Processing Guidelines".

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT [EVONIK-HP@EVONIK.COM](mailto:EVONIK-HP@EVONIK.COM) OR VISIT OUR PRODUCT AT [WWW.INDUSTRIAL.VESTAKEEP.COM](http://WWW.INDUSTRIAL.VESTAKEEP.COM)

### Key Features

#### Processing

Injection molding

#### Delivery form

Pellets, Granules

#### Resistance to

Heat (thermal stability), Fire / burn

#### Conformity

Food contact

#### Additives

Unfilled

<b>Mechanical properties ISO</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Tensile modulus	<b>3500</b>	MPa	ISO 527
Tensile strength	<b>95</b>	MPa	ISO 527
Yield stress	<b>95</b>	MPa	ISO 527
Yield strain	<b>5</b>	%	ISO 527
Stress at break	<b>77</b>	MPa	ISO 527
Nominal strain at break, tB	<b>30</b>	%	ISO 527
Charpy impact strength, +23°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	<b>N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	<b>7</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-
Charpy notched impact strength, -30°C	<b>6</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Type of failure	<b>C</b>	-	-

<b>Thermal properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Melting temperature	<b>340</b>	°C	ISO 11357-1/-3
Vicat softening temperature A, 10 N, 50 K/h	<b>335</b>	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	<b>305</b>	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	<b>60</b>	E-6/K	ISO 11359-1/-2
Melting Temperature	<b>340</b>	°C	ASTM D 3418

<b>Physical properties</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>1300</b>	kg/m <sup>3</sup>	ISO 1183
Density	<b>1300</b>	kg/m <sup>3</sup>	ASTM D 792

<b>Burning Behav.</b>	<b>dry</b>	<b>Unit</b>	<b>Test Standard</b>
Burnin behav. at thickness h	<b>V-0</b>	class	IEC 60695-11-10
Thickness tested	<b>3.2</b>	mm	-

**Electrical properties**

	dry	Unit	Test Standard
Relative permittivity, 1MHz	<b>2.8</b>	-	IEC 62631-2-1
Dielectric strength, AC, S20/P50	<b>16</b>	kV/mm	Sim. to IEC 60243-1
CTI, test solution A, 50 drops value	<b>200</b>	-	IEC 60112
Assessment of the insulation group	<b>III a</b>	-	DIN EN 60664-1

**Rheological properties**

	dry	Unit	Test Standard
Melt volume-flow rate, MVR	<b>10</b>	cm <sup>3</sup> /10min	ISO 1133
Temperature	<b>380</b>	°C	-
Load	<b>5</b>	kg	-
Molding shrinkage, parallel	<b>0.9</b>	%	ISO 294-4, 2577
Molding shrinkage, normal	<b>1.1</b>	%	ISO 294-4, 2577

**Test specimen production**

	dry	Unit	Test Standard
Injection Molding, melt temperature	<b>380</b>	°C	ISO 294
Injection Molding, mold temperature	<b>180</b>	°C	ISO 294
Injection Molding, injection velocity	<b>200</b>	mm/s	ISO 294

**Characteristics**
**Special Characteristics**

Semi-crystalline, High viscosity

**Color**

Black

**Chemical Resistance**

General chemical resistance

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

\* is a registered trademark of Evonik Industries AG or one of its subsidiaries

**Evonik Operations GmbH**  
**Smart Materials**  
**High Performance Polymers**  
 45772 Marl / Germany  
 Tel: +49 2365 49-9878  
[evonik-hp@evonik.com](mailto:evonik-hp@evonik.com)  
[www.plastics-database.com](http://www.plastics-database.com)