

Product Information

VESTAKEEP® 50001XT BK**HIGH VISCOSITY, CROSS-LINKABLE, UNREINFORCED,
UNLUBRICATED POLYETHER ETHER KETONE**

VESTAKEEP® 50001XT BK is a high viscosity, unreinforced, unlubricated polyether ether ketone for injection molding and extrusion and can be cross-linked after processing by heat treatment.

The semi-crystalline polymer features superior property retention at elevated temperatures combined with the chemical resistance of standard PEEK. Parts made from VESTAKEEP® 50001XT BK feature a very high resistance to creep.

VESTAKEEP® 50001XT BK can be processed by common machines for PEEK processing.

VESTAKEEP® 50001XT BK is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

As VESTAKEEP® 50001XT BK is a reactive system we recommend low melt temperatures and short cycle times. Please contact us so our experts can develop the right solution for application together with you.

Inside the original and undamaged packaging, the product has a shelf life of at least 2 years when stored in dry rooms at temperatures not exceeding 30°C.

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM OR VISIT OUR PRODUCT AT WWW.INDUSTRIAL.VESTAKEEP.COM

Key Features**Industrial Sector**

Energy, Oil and Gas

Delivery form

Pellets, Granules

Processing

Injection molding

Resistance to

Heat (thermal stability), Fire / burn

Mechanical properties ISO

Friction coefficient f, parallel

dry

0.27

Unit

-

Test Standard

ISO 7148-2

Wear coefficient k, parallel

2

10E-6 mm³/Nm

ISO 7148-2

Test speed

0.5

m/s

ISO 7148-2

Load	4	MPa	ISO 7148-2
Friction partner	steel	-	ISO 7148-2

Thermal properties	dry	Unit	Test Standard
Melting temperature	352	°C	ISO 11357-1/-3
Glass transition temperature, DSC	178	°C	ISO 11357-1/-2

Physical properties	dry	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183
Moisture content	0.04	Gew.-%	ISO 15512
Density	1300	kg/m ³	ASTM D 792
Shore D hardness, 1s, annealed	90	-	ASTM D 2240

Rheological properties	dry	Unit	Test Standard
Melt volume-flow rate, MVR	7.4	cm ³ /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-

Test specimen production	dry	Unit	Test Standard
Injection Molding, melt temperature	357	°C	ISO 294
Injection Molding, mold temperature	218	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Characteristics

Special Characteristics

Semi-crystalline, Crosslinkable, High viscosity

Color

Black

Features

Creep resistance, Low coefficient of friction

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com