

Product Information

VESTAKEEP® Care M20 G**MEDIUM VISCOSITY, UNREINFORCED POLYETHER ETHER KETONE DESIGNED FOR THE MEDICAL DEVICE INDUSTRY**

VESTAKEEP® Care is the ideal materials for the fabrication of medical devices with short time contact to human blood, tissue or bone for up to 30 days. VESTAKEEP® Care Grades have a good biocompatibility, processability and the option to pigment.

VESTAKEEP® Care M20 G is a medium viscosity, unreinforced polyether ether ketone for injection molding.

The semi-crystalline polymer features superior thermal and chemical resistance.

Biocompatibility of VESTAKEEP® Care

Biocompatibility was tested following ISO10993-1 recommendations for a surface medical device with up to 30 days body contact.

The material fulfills the requirements of USP<88> class VI.

Tests were performed by independent, certified laboratories.

Biocompatibility tests for VESTAKEEP® Care:**Processing of VESTAKEEP® Care**

VESTAKEEP® Care resins can be processed using all conventional melt processing techniques such as injection moulding, extrusion, and compression moulding.

VESTAKEEP® Care M20 G can be processed by common machines for thermoplastics. We recommend a melt temperature between 360°C and 380°C during the injection molding process. The mold temperature should be within a range of 160°C to 200°C, preferably 180°C.

Our technical experts would appreciate to give you support regarding the special requirements for the processing of VESTAKEEP® Care M20 G.

Delivery of VESTAKEEP® Care

VESTAKEEP® Care M20 G is supplied as granules in 25 kg boxes with moisture-proof polyethylene liners.

The results shown have been generated from a low number of production lots. Therefore, they are preliminary and not yet the result of a statistical evaluation. Therefore they must not be used to establish specifications.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features

Industrial Sector

Medical Devices

Processing

Injection molding

Delivery form

Pellets, Granules

Optics

Opaque

Resistance to

Heat (thermal stability), Hydrolysis / hot water, Oil / fuels

Conformity

Biocompatibility, Medical application

Additives

Unfilled

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	3700	MPa	ISO 527
Yield stress	100	MPa	ISO 527
Yield strain	5	%	ISO 527
Nominal strain at break, tB	40	%	ISO 527
Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Type of failure	C	-	-
Charpy notched impact strength, -30°C	6	kJ/m ²	ISO 179/1eA
Type of failure	C	-	-

Thermal properties

	dry	Unit	Test Standard
Vicat softening temperature A, 10 N, 50 K/h	335	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	310	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	60	E-6/K	ISO 11359-1/-2

Physical properties

	dry	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183
Density	1300	kg/m ³	ASTM D 792

Burning Behav.

	dry	Unit	Test Standard
Burnin behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	3.2	mm	-

Electrical properties

	dry	Unit	Test Standard
Volume resistivity, V	>1E13	Ohm*m	IEC 62631-3-1
Relative permittivity, 1MHz	2.8	-	IEC 62631-2-1
CTI, test solution A, 50 drops value	200	-	IEC 60112
Assessment of the insulation group	III a	-	DIN EN 60664-1

Rheological properties

	dry	Unit	Test Standard
Melt volume-flow rate, MVR	70	cm ³ /10min	ISO 1133
Temperature	380	°C	-
Load	5	kg	-
Molding shrinkage, parallel	1.1	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

Test specimen production

	dry	Unit	Test Standard
Injection Molding, melt temperature	380	°C	ISO 294
Injection Molding, mold temperature	180	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294

Characteristics
Special Characteristics

Semi-crystalline

Regulatory

US Pharmacopeia Class VI conformity

Color

Natural color

Chemical Resistance

Acid resistance, Alkali resistance, Solvent resistance, Grease resistance, Hydrolytically stable, Oil resistance, Oxidation resistance, General chemical resistance

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com