

Product Information

VESTAKEEP® D 4 R**NATURAL COLORED POLYETHER ETHER KETONE FOR DENTAL APPLICATIONS**

VESTAKEEP® D4 R is natural colored polyether ether ketone (PEEK) rod stock that is especially designed for removable and fixed dentures, crowns and bridges.

Biocompatibility of VESTAKEEP® Dental

For VESTAKEEP® D4 R, biocompatibility has been tested following ISO 10993-1 recommendations for permanent mucous membrane contact.

The composition is optimised for high biocompatibility and superior mechanical, thermal and chemical resistance.

Biocompatibility test reports available for VESTAKEEP® D4 R

Standard	Description
ISO 10993-03	Genotoxicity: Salmonella Typhimurium Reverse Mutation Test (Ames Test)
ISO 10993-05	Cytotoxicity: Quantitative Growth Inhibition Test
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Local Lymph Node Assay
ISO 10993-11	Acute Systemic Toxicity
ISO 10993-11	Subacute / Subchronic Toxicity 14 days
ISO 10993-18	Extraction Tests
USP Class VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation

Delivery of VESTAKEEP® Dental

VESTAKEEP® D4 R rods are available in standard diameter 100 mm and 1000 mm length. Other dimensions are available on request.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM

OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features**Industrial Sector**

Medical Devices

Processing

Machining

Resistance to

Heat (thermal stability), Hydrolysis / hot water, Wear / abrasion, Fatigue resistance, Oil / fuels

Conformity

Biocompatibility, Medical application

Delivery form
Stock shape (rods and plates)

Additives
Unfilled

Optics
Opaque

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	4000	MPa	ISO 527
Yield stress	110	MPa	ISO 527
Yield strain	4.8	%	ISO 527
Nominal strain at break, tB	>50	%	ISO 527
Izod Impact notched, 23°C	5.5	kJ/m ²	ISO 180/1A
Flexural modulus, 23°C	4050	MPa	ISO 178
Flexural strength, 23°C	175	MPa	ISO 178

Thermal properties

	dry	Unit	Test Standard
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	45	E-6/K	ISO 11359-1/-2

Physical properties

	dry	Unit	Test Standard
Density	1300	kg/m ³	ISO 1183
Water absorption	0.4	%	Sim. to ISO 62
Density	1300	kg/m ³	ASTM D 792

Burning Behav.

	dry	Unit	Test Standard
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Optical properties

	dry	Unit	Test Standard
Color L	60	-	CIE
Color a	2.6	-	CIE
Color b	8.5	-	CIE

Characteristics

Special Characteristics

Semi-crystalline

Regulatory

US Pharmacopeia Class VI conformity

Color

Natural color

Delivery form

Rods Ø70-100mm, stan. lengths 1000mm

Chemical Resistance

Acid resistance, Alkali resistance, Solvent resistance, Grease resistance, Hydrolytically stable, Oil resistance, Oxidation resistance, General chemical resistance

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
 45772 Marl / Germany
 Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com