

Product Information

VESTAKEEP® DC 4420 R

WHITE PIGMENTED POLYETHER ETHER KETONE FOR DENTAL APPLICATIONS



VESTAKEEP® DC4420 R is a white pigmented polyether ether ketone (PEEK) grade rod stock that is especially designed for removable and fixed dentures, crowns and bridges.

Biocompatibility of VESTAKEEP® Dental

For VESTAKEEP® DC4420 R, biocompatibility has been tested following ISO 10993-1 recommendations for permanent mucous membrane contact.

The compound composition is optimised for high biocompatibility and superior mechanical, thermal and chemical resistance.

Biocompatibility test reports available for VESTAKEEP® DC4420 R

Standard	Description
ISO 10993-03	Genotoxicity: Salmonella Typhimurium Reverse Mutation Test (Ames Test)
ISO 10993-05	Cytotoxicity: Quantitative Growth Inhibition Test
ISO 10993-10	Irritation: Intracutaneous Reactivity
ISO 10993-10	Sensitization: Local Lymph Node Assay
ISO 10993-11	Acute Systemic Toxicity
ISO 10993-11	Subacute / Subchronic Toxicity 14 days
ISO 10993-18	Extraction Tests
USP Class VI	Acute Systemic Toxicity Intracutaneous Reactivity Muscle Implantation

Delivery of VESTAKEEP® Dental

VESTAKEEP® DC4420 R rods are available in different diameters and lengths.

Dimensions of VESTAKEEP® DC4420 R

Diameter	Standard length
6 and 8 mm	3000 mm
100 mm	1000 mm

Other custom dimensions are available on request.

The values presented are typical or average values, they do not constitute a specification.

FOR FURTHER INFORMATION PLEASE CONTACT US AT EVONIK-HP@EVONIK.COM
OR VISIT OUR PRODUCT AT WWW.EVONIK.COM/MEDICAL-TECHNOLOGY

Key Features

Industrial Sector

Medical Devices

Processing

Machining

Delivery form

Stock shape (rods and plates)

Optics

Opaque

Resistance to

Heat (thermal stability), Hydrolysis / hot water, Wear / abrasion, Fatigue resistance

Conformity

Biocompatibility, Medical application

Mechanical properties ISO

	dry	Unit	Test Standard
Tensile modulus	4800	MPa	ISO 527
Yield stress	110	MPa	ISO 527
Yield strain	4	%	ISO 527
Nominal strain at break, tB	10	%	ISO 527
Izod Impact notched, 23°C	5.2	kJ/m ²	ISO 180/1A
Type of failure	C	-	-
Flexural modulus, 23°C	4700	MPa	ISO 178
Flexural strength, 23°C	175	MPa	ISO 178

Thermal properties

	dry	Unit	Test Standard
Temp. of deflection under load A, 1.80 MPa	155	°C	ISO 75-1/-2
Temp. of deflection under load B, 0.45 MPa	210	°C	ISO 75-1/-2
Vicat softening temperature A, 10 N, 50 K/h	335	°C	ISO 306
Vicat softening temperature B, 50 N, 50 K/h	305	°C	ISO 306
Coeff. of linear therm. expansion, 23°C to 55 °C, parallel	45	E-6/K	ISO 11359-1/-2

Physical properties

	dry	Unit	Test Standard
Density	1510	kg/m ³	ISO 1183
Water absorption	0.4	%	Sim. to ISO 62
Density	1510	kg/m ³	ASTM D 792

Optical properties

	dry	Unit	Test Standard
Color L	89	-	CIE
Color a	0.5	-	CIE
Color b	5	-	CIE

Characteristics
Special Characteristics

Semi-crystalline

Regulatory

US Pharmacopeia Class VI conformity

Color

White

Delivery form

Rods Ø6-20mm,stan.lengths 3000mm, Rods
Ø70-100mm,stan.lengths 1000mm

Chemical Resistance

Acid resistance, Alkali resistance, Solvent resistance, Grease
resistance, Hydrolytically stable, Oil resistance, Oxidation
resistance, General chemical resistance

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. Evonik disclaims all representations and warranties, whether express or implied, and shall have no liability for, merchantability of the product or its fitness for a particular purpose (even if Evonik is aware of such purpose), or otherwise. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used.

* is a registered trademark of Evonik Industries AG or one of its subsidiaries

Evonik Operations GmbH
Smart Materials
High Performance Polymers
45772 Marl / Germany
Tel: +49 2365 49-9878
evonik-hp@evonik.com
www.plastics-database.com