

TECAPEEK IM GF30 natural - Stock Shapes

Chemical Designation

PEEK (Polyetheretherketone)

Colour

natural

Density

1.53

Fillers

30% glass fibres

Main features

- good heat deflection temperature
- very good chemical resistance
- very high creep resistant
- hydrolysis and superheated steam resistant
- inherent flame resistance
- very high stiffness
- high dimensional stability
- resistance against high energy radiation

Target Industries

- aircraft and aerospace technology
- Aircraft and Aerospace Interiors
- food engineering
- food processing
- agricultural machinery
- automotive industry
- electrical engineering
- chemical plant engineering
- mechanical engineering
- conveyor technology

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@73°F, 1% Sec	1,406,800	psi	ASTMD 638	(1) ASTM D3846
Tensile strength at yield	@73°F	22,800	psi	ASTMD 638	
Elongation at break	@73°F	2.2	%	ASTMD 638	
Flexural strength	@73°F	33,800	psi	ASTMD 790	
Modulus of elasticity (flexural test)	@73°F	1,495,200	psi	ASTMD 790	
Compression strength	@73°F	31,200	psi	ASTMD 695	
Impact strength (Izod)	@73°F	1.8	ft-lbs/in	ASTMD 256	
Rockwell hardness	M scale	103		ASTMD 785	
Coefficient of friction	@ 68°F, 1200 in/min, 155 psi	0.3		-	
Shear strength	@73°F	14,100	psi	-	1)
Thermal properties	condition	value		test method	comment
Melting temperature		633	°F	-	(1) Obtained from public source
Deflection temperature	@ 264 PSI, 1/4"	600	°F	ASTMD 648	(2) Obtained from public source
Service temperature	Long Term	500	°F	-	1)
Thermal expansion (CLTE)		1.2*10 ⁻⁵	in/in/°F	ASTMD 696	
Thermal conductivity		3.0	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	2)
Other properties	condition	value		test method	comment
Moisture absorption	@73°F, 24 hrs	.11	%	ASTMD 570	
Flammability (UL94)		V0		-	

→ Resin specification:
ASTM D4000-11 PEEK; MIL-P-46183 Ty. II Cl. 3, excp. Elong.
Shapes specification:
ASTM D6262-12 S-PAEK0121

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at