

TECAPEEK® MT natural polyetheretherketone - Stock Shapes

Chemical Designation

PEEK (Polyetheretherketone)

Colour

beige opaque

Density

1.31 g/cm³

Main features

- excellent chemical resistance
- very good stress cracking resistance
- high creep resistance
- hydrolysis and superheated steam resistant
- good machinability
- resistance against high energy radiation
- good slide and wear properties
- very good sterilisable

Target Industries

- food technology
- mechanical engineering
- pharmaceutical industry
- medical technology

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	1% Sec, 73 °F	650,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	16,000	psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	@ 73 °F	16,000	psi	ASTM D 638	(3) Injection molded specimen data obtained from public source
Elongation at yield	@ 73 °F	4.9	%	ASTM D 638	(4) injection molded specimen, data obtained from public source
Elongation at break	@ 73 °F	40	%	ASTM D 638	
Flexural strength	@ 73 °F	26,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	600,000	psi	ASTM D 790	
Compression strength	@ 73 °F 10% strain	17,500	psi	ASTM D 695	
Compression modulus	@ 73 °F	493,000	psi	ASTM D 695	2)
Notched impact strength (Izod)	@ 73 °F	0.95	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	99		ASTM D 785	
Coefficient of friction	@ 68 °F Static, 40 psi	0.20		ASTM D 3702	3)
Coefficient of friction	@ 68 °F, Dynamic 40 psi 50 fpm	0.25		ASTM D 3702	4)
Wear (K) factor	40 psi, 50 fpm	200	*10 ⁻¹⁰ in ³ -min/ft-lb-hr	ASTM D 3702	
Thermal properties	condition	value		test method	comment
Melting temperature		633	°F	-	(1) Injection molded specimen
Deflection temperature	@ 264 psi	320	°F	ASTM D 648	(2) Data obtained from public source
Service temperature	short term	572	°F	-	(3) Injection molded specimen
Service temperature	Long Term	480	°F	-	(4) Injection molded specimen from public source
Thermal expansion (CLTE)	< Tg, along flow	2.5	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	4)
Thermal conductivity		2.01	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	5)
Electrical properties	condition	value		test method	comment
surface resistivity		1.0*10 ¹⁶	Ω/square	ASTM D 257	1)
Volume resistivity	@ 73 °F	4.9*10 ¹⁶	Ω*cm	ASTM D 149	2)
Dielectric strength	0.1" thick IEC 60243-1	630	V/mil	-	3)
Dissipation factor	@ 73 °F, 1 MHz	0.003		DIN IEC 60250	4)
Dielectric constant	@ 73 °F, 1 kHz	2.8		DIN IEC 60250	5)
Other properties	condition	value		test method	comment
Limiting PV		69000	psi-fpm	ASTM D 3702	1)
Moisture absorption	@ saturation, 73 °F	0.45	%	DIN EN ISO 62	2)
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTM D 570	3)
Flammability (UL94)		V0		-	

→ Resin specification:
ASTM D4000-11 PEEK; MIL-P-46183 Ty. I
Shapes specification:
ASTM D6262-12 S-PAEK0111

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing