

TECAPEEK SD black - Stock Shapes

Chemical Designation

PEEK (Polyetheretherketone)

Colour

black opaque

Density

1.72 g/cm³

Main features

- electrically static dissipative
- excellent chemical resistance

Target Industries

- semiconductor technology

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	1,200,000	psi	ASTM D 638	(1) Notched
Tensile strength	@ 73 °F	18,180	psi	ASTM D 638	
Elongation at break	@ 73 °F	2.3	%	ASTM D 638	
Flexural strength	@ 73 °F	19,900	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	957,200	psi	ASTM D 790	
Compression strength	1% / 10% strain	7,200/24,640	psi	ASTM D 695	
Compression modulus	@ 73 °F	617,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.08	ft-lbs/in	ASTM D 256	1)
Rockwell hardness	M scale	106		ASTM D 785	
Shore hardness	D scale	94		ASTM D 2240	
Thermal properties	condition	value		test method	comment
Glass transition temperature		318	°F	-	1)
Melting temperature		638	°F	-	2)
Service temperature	short term	572	°F	-	
Service temperature	long term	500	°F	-	
Thermal expansion (CLTE)	73-140°F, long.	2.78	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	73-212°F, long.	2.78	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	212-302°F, long.	3.89	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	
Electrical properties	condition	value		test method	comment
surface resistivity		10 ⁶ - 10 ⁹	Ω	DIN IEC 60093	
Other properties	condition	value		test method	comment
Water absorption	24hr	0.02	%	ASTM D 570	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at