

TECAPEEK® natural polyetheretherketone - Stock Shapes

Chemical Designation

PEEK (Polyetheretherketone)

Colour

beige opaque

Density

1.31 g/cm³

Main features

- made exclusively from Victrex® resin
- excellent chemical resistance
- high thermal resistance
- good heat deflection temperature
- good machinability
- very good slide and wear properties
- hydrolysis and superheated steam resistant

Target Industries

- aircraft and aerospace technology
- food technology
- oil and gas industry
- chemical plant engineering
- semiconductor technology
- food engineering
- medical technology
- automotive industry
- process engineering
- mechanical engineering

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	1% Sec, 73 °F	650,000	psi	ASTMD 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	16,000	psi	ASTMD 638	(2) Data obtained from public source
Tensile strength at break	@ 73 °F	16,000	psi	ASTMD 638	(3) Injection molded specimen data obtained from public source
Elongation at yield	@ 73 °F	4.9	%	ASTMD 638	(4) injection molded specimen, data obtained from public source
Elongation at break	@ 73 °F	30	%	ASTMD 638	
Flexural strength	@ 73 °F	26,000	psi	ASTMD 790	
Modulus of elasticity (flexural test)	@ 73 °F	600,000	psi	ASTMD 790	
Compression strength	@ 73 °F 10% strain	20,000	psi	ASTMD 695	
Compression strength	@ 73 °F 5% strain	16,000	psi	-	
Compression strength	@ 73 °F 1% strain	3,400	psi	-	
Compression modulus	@ 73 °F	493,000	psi	ASTMD 695	2)
Notched impact strength (Izod)	@ 73 °F	0.95	ft-lbs/in	ASTMD 256	
Rockwell hardness	M Scale	99		ASTMD 785	
Coefficient of friction	@ 68 °F Static, 40 psi	0.20		ASTMD 3702	3)
Coefficient of friction	@ 68 °F, Dynamic 40 psi 50 fpm	.25		ASTMD 3702	4)
Wear (K) factor	40 psi, 50 fpm	200	*10 ⁻¹⁰ in ³ -min/ft-lb-hr	ASTMD 3702	
Thermal properties	condition	value		test method	comment
Melting temperature		633	°F	-	(1) Injection molded specimen
Deflection temperature	@264 psi	320	°F	ASTMD 648	(2) Data obtained from public source
Service temperature	short term	572	°F	-	(3) Injection molded specimen
Service temperature	Long Term	480	°F	-	(4) Injection molded specimen from public source
Thermal expansion (CLTE)	< Tg, along flow	2.5	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1:2	4)
Thermal conductivity		2.01	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	5)
Electrical properties	condition	value		test method	comment
surface resistivity		1.0*10 ¹⁶	Ω/square	ASTMD 257	1)
Volume resistivity	@ 73 °F	4.9*10 ¹⁶	Ω*cm	ASTMD 149	2)
Dielectric strength	0.1" thick IEC 60243-1	630	V/mil	-	3)
Dissipation factor	@ 73 °F, 1 MHz	0.003		DIN IEC 60250	4)
Dielectric constant	@ 73 °F, 1 kHz	2.8		DIN IEC 60250	5)
Other properties	condition	value		test method	comment
Limiting PV		69000	psi-fpm	ASTMD 3702	1)
Moisture absorption	@ saturation, 73 °F	0.45	%	DIN EN ISO 62	2)
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTMD 570	3)
Flammability	3 mm	pass		FAR 25.853	3)
Flammability (UL94)		V0		-	4)

→ Resin specification: