

AKROTEK® PRELIMINARY

PK-VM GF 20 natural (8681)

PK GF20

AKROTEK® PK-VM GF 20 natural (8681) is a 20% glass fibre reinforced Polyketone with average stiffness and strength. Due to its very good media resistance, the material is suitable for use in applications that carry cooling water. This type was developed as the successor to PK-VM GF 20 natur (5992) in order to meet the requirements for a larger processing window during processing.

Features

hydrolysis / chemically stabilised

Properties

Modulus

5.700 MPa

Strength

117 MPa

Impact

65 kJ/m²

Mechanical Properties

Tensile modulus

ISO 527-2

1 mm/min | d.a.m.

5700 MPa

Tensile stress at break

ISO 527-2

5 mm/min | d.a.m.

117 MPa

Tensile strain at break

ISO 527-2

5 mm/min | d.a.m.

3,6 %

Charpy impact strength

ISO 179-1/1eU

23°C | d.a.m.

65 kJ/m²

Charpy notched impact strength

ISO 179-1/1eA

23°C | d.a.m.

12 kJ/m²

Thermal Properties

Melting temperature

ISO 11357-3

DSC, 10K/min

220 °C

Flammability


Flammability UL 94	1,6 mm Wall thickness	HB Class
Burning rate (<100 mm/min) FMVSS 302	> 1 mm Thickness	+

General Properties

Density ISO 1183	23°C	1,40 g/cm³
Humidity absorption ISO 1110	70°C, 62% r.H.	0,6 - 0,7 %
Molding shrinkage ISO 294-4	flow	0,4 - 0,6 %
	transverse	0,9 - 1,1 %

Processing

The values mentioned are recommendations. We only recommend desiccant / dry air dryers or vacuum dryers. Too long a drying time and the resulting residual moisture content below the lower limit can lead to filling problems and surface defects. The specified drying time refers to closed and undamaged bagged material. When processing from previously opened bags or from octabins with polyolefin inliners, a longer drying time may be necessary. It is recommended to check the residual moisture content after the drying process.



D	Drying time	0 - 4 h
	Drying temperature ($\tau \leq -30^{\circ}\text{C}$)	80 °C
	Processing moisture	0,02 - 0,1 %
1	Feed section	60 - 80 °C
2	Temperature Zone 1 - Zone 4	220 - 260 °C
3	Nozzle temperature	230 - 260 °C
4	Melt temperature	230 - 260 °C
5	Mold temperature	60 - 120 °C
→	Holding pressure, spec.	300 - 800 bar
←	Back pressure, spec.	30 - 70 bar
	Injection speed	medium to high
	Screw speed	8 - 15 m/min



Polyketones crosslink depending on time and temperature, crosslinking is noticed by an increase of viscosity and/or dark spots in natural colored compounds. The melt temperature should be at or below 260 °C and under no circumstances go beyond 270 °C because crosslinking speed will increase. The use of a hot runner system is not recommended when processing polyketone. However, if it is used, it should be noted that the residence time in the barrel including the hot runner should not exceed 10 min. If interruptions of more than 10 minutes are expected, the barrel and hot runner need to be purged and cleaned with polyolefins. The molding machine needs to be purged with polyolefins before and after processing of AKROTEK® PK! There is a risk of cross linking caused by reactions with POM or PA as well as unsuitable masterbatches or cleaning compounds! Crosslinking is noticed by an increase of viscosity and or dark spots in natural colored compounds. In this case purge immediately with polyolefins. Further processing instructions are available on request.