

TECAPEEK® MT natural polyetheretherketone - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

beige opaque

Density

1.31 g/cm³

Main features

- excellent chemical resistance
- very good stress cracking resistance
- high creep resistance
- hydrolysis and superheated steam resistant
- good machinability
- resistance against high energy radiation
- good slide and wear properties
- very good sterilisable

Target Industries

- food technology
- mechanical engineering
- pharmaceutical industry
- medical technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	1% Sec, 73 °F	650,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	16,000	psi	ASTM D 638	(2) Injection molded specimen data obtained from public source
Tensile strength at break	@ 73 °F	8,900	psi	ASTM D 638	(3) injection molded specimen, data obtained from public source
Elongation at yield (tensile test)	@ 73 °F	4.9	%	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	30	%	ASTM D 638	
Flexural strength	@ 73 °F	26,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	600,000	psi	ASTM D 790	
Compression strength	@ 73 °F 10% strain	20,000	psi	ASTM D 695	
Compression modulus	@ 73 °F	493,000	psi	ASTM D 695	1)
Notched impact strength (Izod)	@ 73 °F	0.95	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	99		ASTM D 785	
Coefficient of friction	@ 68 °F Static, 40 psi	0.20		ASTM D 3702	2)
Coefficient of friction	@ 68 °F, Dynamic 40 psi 50 fpm	0.25		ASTM D 3702	3)
Wear (K) factor	40 psi, 50 fpm	200	*10 ⁻¹⁰ in ³ -min/ft-lb-hr	ASTM D 3702	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		633	°F	-	(1) Injection molded specimen
Deflection temperature	@264 psi	320	°F	ASTM D 648	1) (2) Injection molded specimen
Service temperature	Long Term	480	°F	-	2) (3) Data obtained from public source
Service temperature	short term	572	°F	-	3) (4) Injection molded specimen from public source
Thermal expansion (CLTE)	< Tg, along flow	2.5	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	4) (5) Injection molded specimen from public source
Thermal conductivity		2.01	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	5)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.0*10 ¹⁶	Ω/square	ASTM D 257	1) (1) Injection molded specimen
volume resistance	@ 73 °F	4.9*10 ¹⁶	Ω*cm	ASTM D 149	2) (2) Injection molded specimen
Dielectric strength	0.1" thick IEC 60243-1	630	V/mil	-	3) (3) Injection molded specimen from public source
Dissipation factor	@ 73 °F, 1 MHz	0.003		DIN IEC 60250	4) (4) Injection molded data from public source
Dielectric constant	@ 73 °F, 1 kHz	2.8		DIN IEC 60250	5) (5) Injection molded data from public source
Other properties	condition	value	unit	test method	comment
Limiting PV		69000	psi-fpm	ASTM D 3702	1) (1) publicly sourced data
Moisture absorption	@ saturation, 73 °F	0.45	%	DIN EN ISO 62	2) (2) injection molded data, publicly sourced data
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTM D 570	3) (3) Injection molded specimen 3.0mm
Flammability (UL94)		V0		-	3)