

TECAPEEK UD blue - Ultra Detectable - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

dark blue

Density

1.74 g/cm³

Fillers

detectable filler

Main features

- metal detectable
- x-ray detectable

Target Industries

- food processing
- food technology
- engineering for beverage filling systems
- pharmaceutical industry
- heat exchanger
- conveyor technology

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Tensile strength	@ 73°F	12,750	psi	ASTM D 638	
Modulus of elasticity (tensile test)	@ 73°F	772,200	psi	ASTM D 638	
Elongation at yield (tensile test)	@ 73°F	3.43	%	ASTM D 638	
Elongation at break (tensile test)	@ 73°F	4.13	%	ASTM D 638	
Flexural strength	@ 73°F	21,230	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73°F	728,400	psi	ASTM D 790	
Compression strength	@ 73°F 10% strain	21,235	psi	ASTM D 695	
Compression modulus	@ 73°F	536,730	psi	ASTM D 695	
Impact strength (Izod)	@ 73°F	.79	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73°F M scale	101	%	ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		644	°F	-	
Service temperature	Maximum Short Term	572	°F	-	
Service temperature	Maximum Long Term	500	°F	-	
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Flammability (UL94)		V0		-	