

## Technical Data Sheet

### Polyman ABS M/TK K1516 GRY 61345



Acrylonitrile Butadiene Styrene

#### Product Description

ABS standard grade with higher softening temperature

**Processing Method** Injection Molding

**Resin ID** ABS

| Typical Properties                                                  | Nominal Value | Units                   | Test Method   |
|---------------------------------------------------------------------|---------------|-------------------------|---------------|
| <b>Physical</b>                                                     |               |                         |               |
| Melt Volume Flow Rate, (220 °C/10.0 kg)                             | 23            | cm <sup>3</sup> /10 min | ISO 1133      |
| Density, (Method A)                                                 | 1.05          | g/cm <sup>3</sup>       | ISO 1183      |
| <b>Mechanical</b>                                                   |               |                         |               |
| Tensile Stress at Yield, (Type 1A, 50 mm/min)                       | 52.0          | MPa                     | ISO 527-2     |
| Tensile Strain at Yield, (Type 1A, 50 mm/min)                       | 2.5           | %                       | ISO 527-2     |
| Tensile Modulus, (1 mm/min, Type 1A)                                | 2500          | MPa                     | ISO 527-1     |
| <b>Impact</b>                                                       |               |                         |               |
| Charpy Impact Strength - Notched                                    |               |                         |               |
| (23 °C, Type 1, Edgewise, Notch A)                                  | 15            | kJ/m <sup>2</sup>       | ISO 179       |
| (-30 °C, Type 1, Edgewise, Notch A)                                 | 7.0           | kJ/m <sup>2</sup>       | ISO 179       |
| Charpy Impact Strength - Unnotched                                  |               |                         |               |
| (23 °C, Type 1, Edgewise)                                           | No Break      |                         | ISO 179       |
| (-30 °C, Type 1, Edgewise)                                          | 80            | kJ/m <sup>2</sup>       | ISO 179       |
| <b>Hardness</b>                                                     |               |                         |               |
| Ball Indentation Hardness, (H 358/30)                               | 105           | MPa                     | ISO 2039-1    |
| <b>Thermal</b>                                                      |               |                         |               |
| Vicat Softening Temperature, (B (50N), 50 °C/h)                     | 98.0          | °C                      | ISO 306       |
| Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise) | 96.0          | °C                      | ISO 75-2/B    |
| Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise) | 92.0          | °C                      | ISO 75-2/A    |
| <b>Electrical</b>                                                   |               |                         |               |
| Volume Resistivity                                                  | >1.0E+13      | ohm*m                   | IEC 62631-3-1 |
| Surface Resistivity                                                 | >1.0E+15      | ohm                     | IEC 60093     |
| <b>Flammable</b>                                                    |               |                         |               |
| Burning Rate                                                        |               |                         |               |
| (2.00 mm)                                                           | <100          | mm/min                  | ISO 3795      |
| (2.00 mm)                                                           | <100          | mm/min                  | FMVSS 302     |

|                              |        |                      |  |
|------------------------------|--------|----------------------|--|
| Glow Wire Flammability Index |        |                      |  |
| (1.5 mm)                     | 650 °C | IEC 60695-2-12       |  |
| (3.0 mm)                     | 650 °C | IEC 60695-2-12       |  |
| UL Information               |        |                      |  |
| Flammability Classification  |        |                      |  |
| (1.5 mm)                     | HB     | IEC 60695-11-10, -20 |  |
| (3.0 mm)                     | HB     | IEC 60695-11-10, -20 |  |
| UL File Number               | E86615 |                      |  |