

Technical Data Sheet

Ronfalin ABS 1334 U GRM60275

Acrylonitrile Butadiene Styrene

Product Description

General purpose ABS Compound

Processing Method	Injection Molding
Attribute	Good Flow
Resin ID	ABS

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (220 °C/10.0 kg)	22	cm ³ /10 min	ISO 1133
Density, (Method A)	1.04	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	49.0	MPa	ISO 527-2
Nominal Tensile Strain at Break, (50 mm/min, Type 1A)	16	%	ISO 527-2
Flexural Modulus, (2.0 mm/min)	2900	MPa	ISO 178
Tensile Strain at Yield, (Type 1A, 50 mm/min)	3.1	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 50 mm/min)	37.0	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2600	MPa	ISO 527-1
Flexural Stress, (2.0 mm/min, 4.7%)	83.0	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	17	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	9.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	No Break		ISO 179
(-30 °C, Type 1, Edgewise)	No Break		ISO 179
Hardness			
Ball Indentation Hardness, (H 358/30)	120	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	97.0	°C	ISO 306
(A (10N), 50 °C/h)	104	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	92.0	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	82.0	°C	ISO 75-2/A
Electrical			

Volume Resistivity	1E+15	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI), (Solution A)	600	V	IEC 60112
Surface Resistivity	10000000000 0000	ohm	IEC 60093

Flammable

Burning Rate			
(2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
Glow Wire Ignition Temperature			
(1.5 mm)	700	°C	IEC 60695-2-13
(3.0 mm)	700	°C	IEC 60695-2-13

UL Information

Flammability Classification			
(1.6 mm)	HB		IEC 60695-11-10, -20
(3.2 mm)	HB		IEC 60695-11-10, -20

Injection Parameters	Nominal	
	Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	230 to 250	°C
Mold Temperature	40 to 80	°C