

Technical Data Sheet

Icorene N1016-500 NAT



Ethylene Vinyl Acetate

Product Description

Icorene N1016 is a premium copolymer of ethylene vinyl acetate specifically designed for the preparation of masterbatch and textile bonding. The powder form can achieve better colour developments or additive dispersion in a masterbatch than the pellet form. The vinyl acetate content is about 28%. This grade can be used in various applications such as hot melt adhesives with a maximum processing temperature of 200°C.

Attribute	Copolymer; Dispersible; Food Contact Acceptable; Good Colorability; Heat Stabilized
Forms	Powder
Additive	Heat Stabilizer
Application	Adhesives; Masterbatch

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	150	g/10 min	ASTM D1238
Density, (Internal Method)	0.948	g/cm ³	ASTM D1505
Vinyl Acetate Content, (Internal Method)	28.0	wt %	
Mechanical			
Tensile Elongation at Break	>100	%	ASTM D638
Tensile Modulus	15	MPa	ASTM D638
Hardness			
Durometer Hardness, (Shore A)	72		ASTM D2240
Thermal			
Peak Melting Temperature	66	°C	ASTM D3418
Additional Information			
Continuous Use Temperature, (No Standard)	<200	°C	ASTM D794
Injection Parameters			
Processing (Melt) Temp	<200	°C	