

Technical Data Sheet

Alathon L5485

High Density Polyethylene



Product Description

Alathon L5485 is a medium molecular weight, high density polyethylene copolymer for use in blown film applications. Typical applications include general-purpose HDPE film applications such as overwrap, laminating base films, food packaging and oriented tapes.

Application	Bags & Pouches; Food Packaging Film; Lamination Film; Secondary Packaging
Market	Flexible Packaging
Processing Method	Blown Film
Attribute	General Purpose; Good Organoleptic Properties; High Density; Low Gel

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	0.85	g/10 min	0.85	g/10 min	ASTM D1238
Density, (23 °C)	0.954	g/cm ³	0.954	g/cm ³	ASTM D1505
Film					
Tensile Strength at Break					
MD	7900	psi	54.5	MPa	ASTM D882
TD	3400	psi	23.4	MPa	ASTM D882
Tensile Strength at Yield					
MD	3700	psi	25.5	MPa	ASTM D882
TD	3800	psi	26.2	MPa	ASTM D882
Tensile Elongation at Break					
MD	700	%	700	%	ASTM D882
TD	750	%	750	%	ASTM D882
Secant Modulus					
MD	117000	psi	810	MPa	ASTM D882
TD	153000	psi	1050	MPa	ASTM D882
Elmendorf Tear Strength					
MD	36	g	36	g	ASTM D1922
TD	1000	g	1000	g	ASTM D1922