



## Technical Data Sheet

### HDPE-150F

High Density Polyethylene

#### Product Description

HDPE-150F are use in a broad range of specialty applications. HDPE-150F powders combine the unique properties of a polyolefin resin with a small particle size.

|                    |   |
|--------------------|---|
| <b>Forms</b>       | Powder  |
| <b>Appearance</b>  | Natural Color   |
| <b>Application</b> | Automotive Applications; Colour Concentrates; Industrial Applications; Structural Parts |

| Typical Properties                     | Nominal Value | Units             | Test Method |
|--|---------------|-------------------|-------------|
| <b>Physical</b>                        |               |                   |             |
| Melt Flow Rate, (190 °C/2.16 kg)       | 10            | g/10 min          | ASTM D1238  |
| Density                                | 0.952         | g/cm <sup>3</sup> | ASTM D1505  |
| <b>Mechanical</b>                      |               |                   |             |
| Tensile Elongation at Yield            | 400           | %                 | ASTM D638   |
| Tensile Strength at Break              | 11.7          | MPa               | ASTM D638   |
| Flexural Modulus                       | 1100          | MPa               | ASTM D790   |
| <b>Impact</b>                          |               |                   |             |
| Ductile/Brittle Transition Temperature | <-76.1        | °C                | ASTM D746   |
| <b>Hardness</b>                        |               |                   |             |
| Durometer Hardness                     | 66            |                   | ASTM D2240  |
| <b>Thermal</b>                         |               |                   |             |
| Vicat Softening Temperature            | 125           | °C                | ASTM D1525  |
| Peak Melting Temperature               | 134           | °C                | ASTM D3418  |
| <b>Additional Information</b>          |               |                   |             |
| Average Particle Size                  |               |                   |             |
| Moisture Content                       | <0.1          | %                 |             |

## Notes

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.