

Technical Data Sheet

Icorene 1741 BLK 9001



High Density Polyethylene

Product Description

Icorene 1741 BLACK 9001 is a metallocene high density polyethylene specifically developed for use in rotational moulding. This grade is designed for use in many different rotomoulding applications. It has good overall mouldability, high rigidity and very good toughness.

Processing Method	Rotomolding
Attribute	Good Impact Resistance; Good Moldability; Good Toughness; High Rigidity; UV Resistant
Forms	Powder
Appearance	Black
Additive	UV Stabilizer
Application	Tanks; Thick-walled Parts

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	4.0	g/10 min	ASTM D1238
Density	0.94	g/cm ³	ASTM D1505
Mechanical			
Tensile Strength at Yield	20.0	MPa	ISO 527-2
Flexural Modulus	800	MPa	ASTM D790
Tensile Elongation at Break	800	%	ISO 527-2
Impact			
Drop Impact Resistance, (-20 °C)	180	J/cm	ISO 6603-2
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa)	65	°C	ISO 75-2/B
Melting Temperature	126	°C	ISO 11357

Notes

These are typical property values not to be construed as specification limits.

Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.