

Technical Data Sheet

Lupolen 3426J

Low Density Polyethylene

Product Description

Lupolen 3426 J is an additivated, low density polyethylene. It contains slip and anti-blocking agent. It is characterized by a good processability and high stiffness. LyondellBasell customers report that *Lupolen 3426 J* is used in hygiene film and that films made from *Lupolen 3426 J* exhibit a glossy surface finish. It is delivered in pellet form.

This product is not intended for use in medical and pharmaceutical applications.

Application	Food Packaging Film; Hygiene Film; Lamination Film
Market	Flexible Packaging
Processing Method	Blown Film; Cast Film
Attribute	Good Processability; High Gloss; Low Friction; Superior Optical Properties; Unspecified Antiblocking; Unspecified Slip

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	3.0	g/10 min	ISO 1133-1
Density	0.934	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	480	MPa	ISO 527-1, -2
Tensile Stress at Yield	16	MPa	ISO 527-1, -2
Film			
Dart Drop Impact Strength, F50	90	g	ASTM D1709
Tensile Strength			
MD	19	MPa	ISO 527-1, -3
TD	16	MPa	ISO 527-1, -3
Tensile Strain at Break			
MD	450	%	ISO 527-1, -3
TD	600	%	ISO 527-1, -3
Coefficient of Friction	<0.2		ISO 8295
Impact			
Failure Energy	3	J/mm	DIN 53373
Thermal			
Vicat Softening Temperature, (A/50)	109	°C	ISO 306
Peak Melting Point	119	°C	ISO 11357-3
Optical			
Haze, (50 µm)	<10	%	ASTM D1003

Gloss		
(20°)	>75	ASTM D2457
(60°)	>110	ASTM D2457
Additive		
Slip, Erucamide	650 ppm	LYB Method
Antiblock, Natural Silica	550 ppm	ISO 3451-1
Additional Information		
Test Specimen	Film	
Film properties tested using 50 µm thickness blow n film extruded at a melt temperature of 170°C and a blow-up ratio of 2.5:1.		
Processing Parameters		
Extrusion Temperature	150-190 °C	