

Technical Data Sheet

Polyaxis LLP3550-2A919G GREY 179



Linear Low Density Polyethylene

Product Description

Polyaxis LLP 3550 is a linear low density polyethylene intended for the rotational molding industry. Offers excellent ESCR and toughness.

Processing Method	Rotomolding
Attribute	Good ESCR (Environmental Stress Cracking Resistance); Good Toughness; Hexene Comonomer; UV Resistant
Forms	Powder
Appearance	Colors Available
Application	Agricultural Tanks; Outdoor Applications; Pallets; Septic Tanks; Toys

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (190 °C/2.16 kg)	5.0	g/10 min	ASTM D1238
Density - Specific Gravity	0.935	g/cm ³	ASTM D1505
Mechanical			
Tensile Elongation at Yield, (51 mm/min)	20	%	ASTM D638
Tensile Strength at Yield, (50 mm/min, Rotational Molded)	16.5	MPa	ASTM D638
Environmental Stress Crack Resistance			
(Compression Molded, F50, 100% Igepal)	>980	hr	ASTM D1693
(Compression Molded, F50, 10% Igepal)	60.0	hr	ASTM D1693
Flexural Modulus, (Rotational Molded, 1% Secant)	621	MPa	ASTM D790
Impact			
Impact Strength			
(-40 °C, 3.18 mm, Rotational Molded)	81	J	ARM
(-40 °C, 6.35 mm, Rotational Molded)	217	J	ARM
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	36.1	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	50	°C	ASTM D648
Peak Melting Temperature	126	°C	ASTM D3418