## **Technical Data Sheet**

## Petrothene GA694192

Linear Low Density Polyethylene

## **Product Description**

*Petrothene* GA694192 is a pelletized LLDPE copolymer resin selected by customers for injection molding. Typical applications include lids and thin-walled items that require high flow and short cycle times. GA694192 exhibits excellent flow, warp resistance and surface appearance.

Application	Lids
Market	Rigid Packaging
Processing Method	Injection Molding

T 1 1 B	Nominal	English	Nominal	SI	<b>T</b>
Typical Properties	Value	Units	Value	Units	Test Method
Physical					
Melt Flow Rate, (190 °C/2.16 kg)	160	g/10 min	160	g/10 min	ASTM D1238
Density, (23 °C)	0.933	g/cm³	0.933	g/cm³	ASTM D1505
Spiral Flow	29.0	in	73.0	cm	LYB Method
Mechanical					
Flexural Modulus					
(1% Secant)	94000	psi	650	MPa	ASTM D790
(2% Secant)	83000	psi	570	MPa	ASTM D790
Tensile Strength at Break, (23 °C)	2300	psi	16	MPa	ASTM D638
Tensile Strength at Yield, (23 °C)	2500	psi	17	MPa	ASTM D638
Tensile Elongation at Yield, (23 °C)	10	%	10	%	ASTM D638
Hardness					
Shore Hardness, (Shore D)	62		62		ASTM D2240
Thermal					
Vicat Softening Temperature	198	°F	92	°C	ASTM D1525
Low Temperature Brittleness, F₅₀	19	°F	-7	°C	ASTM D746
Deflection Temperature Under Load, (66 psi, Unannealed)	127	°F	53	°C	ASTM D648

