



Technical Data Sheet

Alcryn ALC - 4670NCNAT

Melt Processable Rubber

Product Description

Alcryn® 4670 NC is a Melt Processable Rubber (MPR) product. It can be processed by blow molding, calendering, compression molding, or extrusion and is available in Asia Pacific, Europe, or North America. Applications of Alcryn® 4670 NC include engineering/industrial parts, hose/tubing, wire & cable, fabrics/fibers and handles.

Processing Method	Blow Molding; Calendering; Compression Molding; Extrusion; Vacuum Forming
Attribute	Fast Molding Cycle; High Heat Resistance; Noise Damping; Oil Resistant; Ozone Resistant; Recyclable Material; Vibration Damping
Forms	Pellets
Appearance	Natural Color
Application	Cable Jacketing; Coating Applications; Fabric Coatings; Flexible Grips; Gaskets; General Purpose; Handles; Hose; Overmolding; Profiles; Seals; Tubing; Weatherstripping; Wire & Cable

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
Physical					
Density	1.25	g/cm ³	1.25	g/cm ³	ISO 1183
Change in Volume					
(in ASTM #1 Oil, 100 °C, 168 hr)	-17	%	-17	%	ASTM D471
(in Water, 100 °C, 168 hr)	11	%	11	%	ASTM D471
(in Reference Fuel B, 24 °C, 168 hr)	16	%	16	%	ASTM D471
(in ASTM #3 Oil, 100 °C, 168 hr)	17	%	17	%	ASTM D471
Melt Viscosity, (190 °C, 300 sec ⁻¹)			500	Pa·s	ASTM D3835
Mechanical					
Tensile Modulus, (23 °C)	570	psi			ASTM D638
Tensile Strength at Yield, (2 in/min) (.0750 in. Compression Molded)	1280	psi			ASTM D638
Tensile Elongation at Break, (23 °C) (.0750 in. Compression Molded)	440	%	440	%	ASTM D638
Change in Ultimate Elongation in Air, (121 °C, 168 hr)	380	%	380	%	ASTM D471
Torsion Modulus					
(24 °C, 1.9 mm)	350	psi			ASTM D1043
(-20 °C, 1.9 mm)	4000	psi			ASTM D1043
Tensile Set	9	%	9	%	ASTM D412
Clash-Berg Modulus, (-21 °C)			68.9	MPa	ASTM D1043
Tear Strength			38.5	kN/m	ASTM D624

Hardness			
Shore Hardness, (Shore A, 15 sec)	70	70	ASTM D2240
Change in Shore Hardness in Air, (Shore A, 125 °C, 168 hr)	64	64	ISO 188
Change in Durometer Hardness in Air, (Shore A, 125 °C, 168 hr)	64	64	ASTM D471
Thermal			
Low Temperature Brittleness		-60 °C	ASTM D746
Additional Information			
Compression Set			
(24 °C, 22 hr, Method B)	21 %	21 %	ASTM D395 B
(100 °C, 22 hr, Method B)	74 %	74 %	ASTM D395 B
Extrusion Parameters			
	Nominal Value	English Units	Nominal Value SI Units
Melt Temperature			177 °C