

Technical Data Sheet

Schulamid 6 GB30 BUE965190



Polyamide 6

Product Description

Schulamid 6 GB30 BUE965190 is a Polyamide 6 Glass Bead, 30% filled material and is typically used in Injection Molding applications. Features include: Good Dimensional Stability, Good Surface Finish, Low Warpage, and Oil Resistant.

Processing Method Injection Molding

Attribute Good Dimensional Stability; Good Surface Finish; Low Warpage; Oil Resistant

Filler/Reinforcement Glass Bead, 30%

Resin ID PA6-GB30

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density, (Method A)	1.36	g/cm ³	ISO 1183
Viscosity Number	145	cm ³ /g	ISO 307
Mechanical			
Flexural Strain at Flexural Strength	6.5	%	ISO 178
Tensile Strain at Break			
(Type 1A, 5 mm/min)	10	%	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	50	%	ISO 527-2
Flexural Modulus	3000	MPa	ISO 178
Tensile Stress at Break			
(Type 1A, 5 mm/min)	70.0	MPa	ISO 527-2
(Type 1A, 5 mm/min) - Conditioned	34.0	MPa	ISO 527-2
Tensile Modulus			
(1 mm/min, Type 1A)	4000	MPa	ISO 527-1
(1 mm/min, Type 1A) - Conditioned	1200	MPa	ISO 527-1
Flexural Stress	100	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise, Notch A) - Conditioned	14	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	35	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	28	kJ/m ²	ISO 179
(23 °C, Type 1, Edgewise) - Conditioned	No Break		ISO 179
Hardness			

Ball Indentation Hardness			
(H 358/30)	165	MPa	ISO 2039-1
(H 358/30) - Conditioned	105	MPa	ISO 2039-1
Ball Pressure Test, (105 °C)	Pass		IEC 60695-10-2

Thermal

Vicat Softening Temperature			
(B (50N), 50 °C/h)	200	°C	ISO 306
(A (10N), 50 °C/h)	215	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	180	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	68.0	°C	ISO 75-2/A
RTI Elec			
(1.5 mm)	65.0	°C	UL 746B
(3.0 mm)	65.0	°C	UL 746B
RTI Imp			
(1.5 mm)	65.0	°C	UL 746B
(3.0 mm)	65.0	°C	UL 746B
RTI Str			
(1.5 mm)	65.0	°C	UL 746B
(3.0 mm)	65.0	°C	UL 746B

Electrical

Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
- Conditioned	>1.0E+10	ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	450	V	IEC 60112
Surface Resistivity	>1.0E+15	ohm	IEC 60093
- Conditioned	>1.0E+12	ohm	IEC 60093

Flammable

Burning Rate			
(2.00 mm)	80	mm/min	FMVSS 302
(2.00 mm)	80	mm/min	ISO 3795
Glow Wire Flammability Index			
(1.5 mm)	650	°C	IEC 60695-2-12
(3.0 mm)	650	°C	IEC 60695-2-12

Additional Information

Water Absorption 23C/50RH	1.9	%	ISO 62
---------------------------	-----	---	--------

UL Information

Flammability Classification			
(1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20
UL File Number	E86615		

Injection Parameters		Nominal Value	Units
Drying Time		3.0 to 4.0	hr
Drying Temperature		80	°C
Suggested Max Moisture		0.040 to 0.10	%
Processing (Melt) Temp		250 to 280	°C
Mold Temperature		60 to 100	°C