

Technical Data Sheet

Vitamide AS11BK 1336/1



Polyamide 66

Product Description

General purpose, medium viscosity, lubricated Polyamide 66. Suitable for a wide range of applications, this grade offers an effective cycle time and a good balance of stiffness and impact strength. Available with enhanced UV (AS21), heat stability (AS31) and cycle time performance (AS41). Colour matched compounds and customer specific performance requirements are available on request.

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Density	1.13	g/cm ³	ISO 1183
Mechanical			
Tensile Strain at Break	20	%	ISO 527-2
Flexural Modulus	2800	MPa	ISO 178
Tensile Stress at Break	75	MPa	ISO 527-2
Flexural Stress	105	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	4.5	kJ/m ²	ISO 179
Notched Izod Impact Strength, (23 °C)	6.0	kJ/m ²	ISO 180
Hardness			
Shore Hardness, (Shore D)	84		ISO 868
Rockwell Hardness, (R-Scale)	120		ISO 2039-2
Ball Indentation Hardness, (H 358/30)	155	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (B (50N), 120 °C/h)	198	°C	ISO 306
Deflection Temperature Under Load Unannealed (0.45 MPa)	223	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	80	°C	ISO 75-2/A
Melting Temperature	260	°C	ISO 11357-3
Electrical			
Dielectric Strength	26	kV/mm	ASTM D149
Comparative Tracking Index (CTI), (Solution A)	525	V	IEC 60112
Surface Resistivity	1E+15	ohm	ASTM D257
Flammable			
Burning Rate, (FMVSS)	<100	mm/min	FMVSS
Glow Wire Flammability Index	850	°C	IEC 60695-2-12
Additional Information			

Molding Shrinkage	1.5	%	ISO 294-4
Water Absorption 23C/50RH	2.3	%	ISO 62
Water Absorption 24h/23C	1.5	%	ISO 62
Water Absorption Sat/23C	8.5	%	ISO 62
UL Information			
Flame Rating, (1.6 mm)	HB		UL 94

Injection Parameters	Nominal	
	Value	Units
Drying Time	3.0 to 4.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	270 to 290	°C
Mold Temperature	60 to 100	°C