

Technical Data Sheet

Hostacom ERC 1122N NATURAL



Polypropylene Compounds

Product Description

Hostacom ERC 1122N NATURAL is a 15% mineral filled, polypropylene copolymer for injection molding. It combines excellent stiffness, scratch resistance and flowability with good impact and dimensional stability. It is typically used for molding of automotive interior trim parts.

Application Interior Automotive Applications

Market Automotive

Processing Method Injection Molding

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ASTM D1238
Density, (23 °C)	1.01	g/cm ³	ISO 1183-1
Mechanical			
Flexural Modulus, (23 °C)	2380	MPa	ISO 178
Tensile Stress at Yield, (23 °C)	28	MPa	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C)	7.0	kJ/m ²	ISO 179
(-30 °C)	2.5	kJ/m ²	ISO 179
Thermal			
Deflection Temperature Under Load			
(0.45 MPa, Unannealed)	110	°C	ISO 75B-1, -2
(1.80 MPa, Unannealed)	60	°C	ISO 75A-1, -2
Additional Information			
Mold Shrinkage			ISO 294-4
Please contact LyondellBasell for shrinkage recommendations.			