

## Technical Data Sheet

### Moplen EP2641



Polypropylene, Impact Copolymer

#### Product Description

Moplen EP2641 is a nucleated heterophasic copolymer used in injection moulding and compounding applications. It exhibits good impact / stiffness balance combined with high fluidity with good organoleptic properties.

Moplen EP2641 is typically used in opaque containers, housewares, toys and in thin wall containers for food packaging (e.g. Margarine tubs, Yoghurt pots etc) and compounding applications

#### Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

<b>Application</b>	Automotive Parts; Housewares; TWIM Food Containers
<b>Market</b>	Compounding; Rigid Packaging
<b>Attribute</b>	Contains Antistat; High Flow; Nucleated

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	70	g/10 min	ISO 1133-1
Density	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Tensile Modulus	1500	MPa	ISO 527-1, -2
Tensile Stress at Yield	25	MPa	ISO 527-1, -2
Tensile Strain at Yield	5	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	5	kJ/m <sup>2</sup>	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m <sup>2</sup>	ISO 179
(-20 °C)	3	kJ/m <sup>2</sup>	ISO 179