

Technical Data Sheet

**Polyfort FPP 30TSHH K2362 BLK**

Polypropylene, Homopolymer

**Product Description**

30% talc filled PP-Homopolymer with long term heat stabilization

**Processing Method** Injection Molding

**Attribute** Heat Stabilized

**Filler/Reinforcement** Talc, 30%

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Volume Flow Rate, (230 °C/2.16 kg)	15	cm <sup>3</sup> /10 min	ISO 1133
Density, (Method A)	1.15	g/cm <sup>3</sup>	ISO 1183
<b>Mechanical</b>			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	30.0	MPa	ISO 527-2
Tensile Strain at Break	2.8	%	ISO 527-2
Flexural Modulus	3900	MPa	ISO 178
Tensile Modulus, (1 mm/min, Type 1A)	3700	MPa	ISO 527-1
Flexural Stress	51	MPa	ISO 178
<b>Impact</b>			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	3.0	kJ/m <sup>2</sup>	ISO 179
Charpy Impact Strength - Unnotched, (23 °C, Type 1, Edgewise)	25	kJ/m <sup>2</sup>	ISO 179
<b>Thermal</b>			
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	70.0	°C	ISO 75-2/A
<b>Electrical</b>			
Volume Resistivity	>1.0E+13	ohm*m	IEC 62631-3-1
Surface Resistivity	>1.0E+15	ohm	IEC 60093
<b>Flammable</b>			
Burning Rate (2.00 mm)	<100	mm/min	ISO 3795
(2.00 mm)	<100	mm/min	FMVSS 302
<b>UL Information</b>			
Flammability Classification (1.5 mm)	HB		IEC 60695-11-10, -20
(3.0 mm)	HB		IEC 60695-11-10, -20
<b>Injection Parameters</b>			
Drying Time	2.0 to 3.0	hr	
Drying Temperature	80	°C	
Processing (Melt) Temp	220 to 260	°C	
Injection Rate	Moderate-Fast		
Mold Temperature	30 to 60	°C	